

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

3. WI564-03

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C08K 5/16, C08G 63/88, C08L 67/02</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/58393</b> <b>(43) International Publication Date:</b> 5 October 2000 (05.10.00)
<b>(21) International Application Number:</b> PCT/US00/05604 <b>(22) International Filing Date:</b> 2 March 2000 (02.03.00)  <b>(30) Priority Data:</b> 60/127,080 31 March 1999 (31.03.99) US 09/505,785 17 February 2000 (17.02.00) US  <b>(71) Applicant:</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).  <b>(72) Inventors:</b> KURIAN, Joseph, Varapadavil; 14 Oak View Drive, Newark, DE 19702 (US). CHANG, Jing, Chung; 12 North Sweetbriar Lane, Columbia, SC 29223 (US).  <b>(74) Agent:</b> MAYER, Nancy, S.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> BR, CA, CN, ID, IN, JP, KR, MX, TR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> LOW EMISSION POLYMER COMPOSITIONS  <b>(57) Abstract</b>  The invention comprises polymer compositions containing 3-hydroxypropanoxy terminated polymer that exhibit reduced levels of degradation product emissions during processing, by contacting the polymer in the molten state with a melt stable, organic nitrogen-containing stabilizing compound, such as polyamide.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CJ	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

**TITLE****LOW EMISSION POLYMER COMPOSITIONS**

5

**FIELD OF THE INVENTION**

10 The invention concerns polymer compositions that exhibit reduced levels of degradation product emissions during processing. This invention further concerns processes for the fabrication of polymer articles with low emissions of polymer degradation products.

**TECHNICAL BACKGROUND**

15 3-Hydroxypropanoxy terminated polymers have the problem of being prone to thermal degradation processes that result in acrolein emissions. Acrolein is an irritant chemical, for which workplace levels are strictly regulated, i.e. to limit its content in the air to be less than 0.1 ppm [AEL].

20 **SUMMARY OF THE INVENTION**

The present invention solves this problem by providing compositions comprising 3-hydroxypropanoxy terminated polymers of improved stability with regard to acrolein emission. The present invention comprises compositions prepared by contacting molten 3-hydroxypropanoxy terminated polymer with an effective amount of a melt stable, organic nitrogen-containing stabilizing compound to reduce the emission of acrolein from said molten polymer.

This invention also comprises a process for the fabrication of polymer articles from 3-hydroxypropanoxy terminated polymers exhibiting low levels of acrolein emissions, which process comprises:

30 a) contacting in the molten state said 3-hydroxypropanoxy terminated polymer with an effective amount of a melt stable, organic nitrogen-containing stabilizing compound to reduce the emission of acrolein from said polymer in the molten state, and

b) fabricating said polymer into said article.

35

**DETAILED DESCRIPTION OF THE INVENTION**

3-Hydroxypropanoxy terminated polymers, i.e., those polymers bearing an end group of the structure  $\text{-O-CH}_2\text{CH}_2\text{CH}_2\text{OH}$ , are prone to degradative

processes when molten that result in the generation and emission of acrolein,  $\text{CH}_2=\text{CHCHO}$ .

3-Hydroxypropanoxy terminated polymers comprise those polymers prepared from 1,3-propanediol or its chemical equivalents. The 1,3-propanediol can be prepared chemically or biologically. For purpose of this specification the term 3-hydroxypropanoxy terminated polymers includes, but is not limited to 1,3-propanediol dicarboxylate polymer, examples of which include poly(trimethylene terephthalate), poly(trimethylene naphthalenedicarboxylate), poly(trimethylene isophthalate) and blends and copolymers thereof. Other dicarboxylic acids useable in the 3-hydroxypropanoxy terminated polymers include 1,4-cyclohexane dicarboxylic acid, 1,3-cyclohexane dicarboxylic acid, succinic acid, glutaric acid, adipic acid, sebacic acid and 1,12-dodecane dioic acid. Depending on the route of synthesis employed in the preparation of the polymers of the present invention, the dicarboxylic acids may be introduced to the polymerization process as the dicarboxylic acids or as the lower dialkyl esters of the dicarboxylic acids, for example, the dimethyl, diethyl, or dipropyl esters of these dicarboxylic acids.

Copolymers useable with the polymers of the present invention typically comprise any of the dicarboxylic acids mentioned above and diols other than 1,3-propanediol, for example, up to 30 mol% of such other diol, based on the total moles of diol present. These diols include ethylene glycol, 1,4-butane diol, 1,2-propanediol, diethylene glycol, triethylene glycol, 1,3-butane diol, 1,5-pentane diol, 1,6-hexane diol, 1,2-, 1,3- and 1,4-cyclohexane dimethanol, and the longer chain diols and polyols made by the reaction product of diols or polyols with alkylene oxides.

When the polymers of the present invention are used in blends, the blend polymer can be prepared from any of the diacids or the diols listed above. A specifically preferred blend comprises poly(ethylene terephthalate) and poly(trimethylene terephthalate).

These polymers have a high molecular weight so as to be commercially useful. Such molecular weight can be characterized by the polymer having an intrinsic viscosity (IV) of at least 0.1 dl/g, determined by measuring the flow time of a solution of known polymer concentration and the flow time of the polymer solvent in a capillary viscometer, as set forth in ASTM D2857.95

The polymer can be a homopolymer or blends and copolymers containing at least 10% of one or more 3-hydroxypropanoxy terminated polymer. For example a blend comprising 90% poly(ethylene terephthalate) and 10% poly(trimethylene terephthalate) - (containing up to 1 weight % of a polyamide

polymer as the stabilizing compound), is within the envisioned scope of the present invention.

The melt stable, organic nitrogen-containing stabilizing compound with which the 3-hydroxypropanoxy terminated polymer is intimately blended is selected from melt stable primary, secondary and tertiary amines, either aliphatic or aromatic, and aliphatic or aromatic amides. Also included are polymers containing such functional groups either as a polymer side chain or in the polymer backbone, e.g., polyamides, and copolymers and blends of polyamides.

When polyamides are employed, they can be linear or branched in chain structure. Examples of linear polyamides include, monomeric polyamides, such as poly(caprolactam), nylon 6, and bis monomeric polyamides, such as poly(hexamethylenediamine adipate), nylon 4,6, nylon 6,6, nylon 6,10, nylon 6,12, nylon 12,12, or their copolymers and blends. Certain aromatic polyamides, for example poly(p-phenylene terephthalamide) and poly(m-phenylene isophthalamide), can also be employed. Polyamides prepared from the use of tri-, tetra- or multifunctional amines, e.g., bis(hexamthylenetriamine) or BHMT can also be used.

To reduce the emission of acrolein from the 3-hydroxypropanoxy terminated polymer, it is only necessary that the stabilizing compound contain nitrogen and be stable in the polymer melt. Preferably, the stabilizing compound will also be in the liquid state in the melt of 3-hydroxypropanoxy terminated polymer so as to be intimately mixed with the polymer. Typically, the compound is of sufficient molecular weight so as to achieve stability in molten 3-hydroxypropanoxy terminated polymer, in which case, the liquid state of the compound will be the molten state. The stabilizing should also not introduce or cause color in the polymer. Polyamides such as described above fulfill all of these characteristics and thus are a preferred class of stabilizing compounds.

While not meaning to be bound by any theory, it is believed that the nitrogen functionality in the melt stable, organic nitrogen-containing stabilizing compound either interacts with the 3-hydroxypropanoxy terminus of the polymer chain, or a degradation product thereof, to hinder or stop degradative pathways that generate acrolein or interacts with generated acrolein on the molecular level to hinder or prevent emission. The reactions between amines (primary, secondary, and tertiary) and aldehydes giving different adducts is well documented in literature. For a review of the reactions between amines and aldehydes, See Rec. Chem. Prog., 29, 85-101 (1968).

The amount of melt stable, organic nitrogen-containing stabilizing compound present in the composition of the present invention is defined as an

amount to be effective in the reduction of acrolein emission. This is generally less than 10% by weight based on the amount of the 3-hydroxypropanoxy terminated polymer present. One percent by weight has been demonstrated to be effective. The range of effective amounts can be from about 0.01% to about 10% by weight.

Articles of manufacture prepared from 3-hydroxypropanoxy terminated polymers, copolymers and blends can include fibers (monocomponent, bicomponent, for example bicomponent with poly(ethylene terephthalate, or multicomponent), filaments, films, castings and moldings. The manufacture of these articles generally require the starting polymer to be in molten form at some stage of the manufacturing process. It is during this molten stage that acrolein emission is most prevalent.

The composition comprising the 3-hydroxypropanoxy terminated polymer and the melt stable, organic nitrogen-containing stabilizing compound can be formed from the 3-hydroxypropanoxy terminated polymer in flake or pellet form mixed with the melt stable, organic nitrogen-containing stabilizing compound in solid form. The resulting mixture can then be melt processed, i.e., in an extruder, to form the intimate polymer mixture. Alternatively, the melt stable, organic nitrogen-containing stabilizing compound can be introduced into and mixed with a molten stream of 3-hydroxypropanoxy terminated polymer. In the case where a polyamide or copolyamide or polyamide blend is used as the melt stable, organic nitrogen-containing stabilizing compound, this material can be dry blended with the 3-hydroxypropanoxy terminated polymer prior to processing or fed as a melt into a melt of the 3-hydroxypropanoxy terminated polymer. Oligomers containing the nitrogen functionality of the melt stable, organic nitrogen-containing stabilizing compound may also be mixed into a melt of the 3-hydroxypropanoxy terminated polymer. The solid phasing of 3-hydroxypropanoxy terminated oligomers can occur in presence of an oligomeric or polymeric nitrogen containing stabilizing compound. In all of these cases, the 3-hydroxypropanoxy terminated polymer and stabilizing compound are in contact with one another when the former is in the molten state. The resultant article fabricated from this melt, such as filament, film or molded article, is then not accompanied by the presence of a detrimental amount of acrolein in the surrounding atmosphere.

In the examples hereafter, spinning tests were conducted in a spinning assembly comprising a conditioning vessel, a screw assembly, a spinning pack comprising a 1050 hole staple spinneret, 39 pounds (17.7 kg) per hour throughput and a polymer residence time about 5 minutes. The screw was shutdown and the

conditioner vessel was cleaned before charging each polymer item. Each polymer item was conditioned for 30 minutes using 160°C recirculating gas before the screw was started up. All samples were taken 30 minutes after the screw system was stable. For the acrolein measurements, NIOSH method NIOSH 2532M was used.

## **EXAMPLES**

### **Comparative Examples 1 and 2**

A sample of poly(trimethylene terephthalate) polymer pellets, prepared via polycondensation of bis(3-hydroxypropyl) terephthalate, having an intrinsic viscosity of 1.02 dl/g, was conducted to a melt spinning apparatus maintained at 274°C. After 30 minutes spinning, air sampling was conducted 4 inches (10.16 cm) below the spinneret and 5 inches (12.7 cm) before the yarn bundle. Samples were taken for 15 minutes (at 1 liter air/minute) and 30 minutes. Results are in the Table 1 as comparative Examples 1 and 2, respectively.

### **Examples 1 and 2**

Spinning was conducted as in Comparative Example 1 except that the feed to the melt spinning assembly consisted of a physical mixture of 99% (by weight) of poly(trimethylene terephthalate - same batch as above) and 1% by weight of a commercial nylon 6 polymer (40 RV, containing 0.025% TiO<sub>2</sub>, obtained from Nylmex, Monterrey, Mexico). Data from 15 minute and 30 minute air samples are in Table 1 as Examples 1 and 2, respectively.

### **Examples 3 and 4**

Spinning was conducted as in Comparative Example 1 (and Example 1) except that the feed to the melt spinning assembly consisted of a physical mixture of 95% (by weight) of poly(trimethylene terephthalate - same batch as above) and 5% by weight of a commercial nylon 6 polymer (40 RV, containing 0.025% TiO<sub>2</sub>, obtained from Nylmex, Monterrey, Mexico). Data from 15 minute and 30 minute air samples are in the Table as Examples 3 and 4, respectively.

TABLE 1

Example No.	Polymer Temp°C	Nylon 6 wt %	Sample Volume liters*	<u>Air Sample</u>	
				Acrolein. µg	Conc. Ppm (µg/g)
Comp. 1	274	0	15	4.73	0.14
Comp. 2	274	0	30	4.98	0.07
1	274	1	15	<0.50	<0.01
2*	274	1	30	<0.50	<0.01
3	274	5	15	<0.50	<0.01
4	274	5	30	<0.50	<0.01

\*air sampling rate = 1 liter/min.

5 These results showed at least about tenfold reduction in acrolein emission occurring during the fabrication of 3-hydroxypropanoxy terminated polymer from the molten state when polyamide was incorporated into the polymer so that it was present in the melt so as to be in contact with the 3-hydroxypropanoxy terminated polymer at the time when acrolein emission would otherwise occur. Similar results can be obtained when other melt stable nitrogen-containing stabilizing compounds are used in place of or in addition to the polyamide.

10



**WHAT IS CLAIMED IS:**

1. A composition prepared by contacting molten 3-hydroxypropanoxy terminated polymer with an effective amount of a melt stable, organic nitrogen-  
5 containing stabilizing compound to reduce the emission of acrolein from said molten polymer.
2. A process for the fabrication of polymer articles from  
3-hydroxypropanoxy terminated polymers exhibiting low levels of acrolein  
10 emission, which process comprises:
  - a) contacting in the molten state said 3-hydroxypropanoxy terminated polymer with an effective amount of melt stable, organic nitrogen-containing stabilizing compound to reduce the emission of acrolein from said polymer in the molten state, and  
15 b) fabricating said polymer into said article.
3. The composition of Claim 1 wherein the melt stable, organic nitrogen-containing stabilizing compound is selected from the group consisting of melt stable, aliphatic or aromatic, primary, secondary and tertiary amines, aliphatic or  
20 aromatic amides and polymers containing such amines or amides either as a polymer side chain or in the polymer backbone.
4. The process of Claim 2 wherein the melt stable, organic nitrogen-containing stabilizing compound is selected from the group consisting of melt  
25 stable, aliphatic or aromatic, primary, secondary and tertiary amines, aliphatic or aromatic amides and polymers containing such amines or amides either as a polymer side chain or in the polymer backbone.
5. The composition of Claim 3 wherein the melt stable, organic  
30 nitrogen-containing stabilizing compound is a polymer containing an amide functional group.
6. The composition of claim 1 when the effective amount of said stabilizing compound is up to 10 weight percent based on the weight of said  
35 polymer
7. The composition of claim 1 wherein said 3-hydroxypropanoxy terminated polymer is 1,3-propandiol dicarboxylate.

# INTERNATIONAL SEARCH REPORT

Inter. Application No

PCT/US 00/05604

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08K5/16 C08G63/88 C08L67/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08K C08G C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 081 591 A (TAKIYAMA EIICHIRO ET AL) 28 March 1978 (1978-03-28) column 3, line 4-46; examples 1-9	1-4, 6
A	US 5 798 433 A (SCHAUHOFF STEPHANIE ET AL) 25 August 1998 (1998-08-25) column 1, line 36 - line 58; claims; examples 5-7	1-7
A	WO 98 23662 A (SHELL INT RESEARCH) 4 June 1998 (1998-06-04) page 6, line 9 -page 7, line 15; claims; table 1	1-7

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

22 June 2000

Date of mailing of the international search report

06/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Friederich, P

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/05604

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4081591 A	28-03-1978	JP 937274 C JP 51146477 A JP 53015517 B DE 2626112 A FR 2314217 A GB 1540661 A IT 1062223 B	26-12-1978 16-12-1976 25-05-1978 30-12-1976 07-01-1977 14-02-1979 20-09-1983
US 5798433 A	25-08-1998	DE 19705249 A CN 1190661 A EP 0859020 A	13-08-1998 19-08-1998 19-08-1998
WO 9823662 A	04-06-1998	AU 5753198 A EP 0941266 A	22-06-1998 15-09-1999